




Technical properties:

Properties	Value	Unit	Standard
Compressive strength 10% deformation	300	KPa	EN 826
Density	35 (+/-15%)	kg/m ³	EN 1602
Thermal conductivity	0,034 (30-60 mm) 0,036 (> 60 mm)	W/m·K	EN 12667 EN 12939
Water absorption	≤0,7	% volumen	EN 12087
Reaction to fire	E	Euroclase	EN 13501-1
Temperature limits	-50/+75	°C	
Coefficient of linear thermal expansion	0,07	mm/m·K	
Capillarity	0		
Dimensions	30,40,50,60,80 & 100 1250x600	mm mm mm	EN 823 EN 822 EN 822
Surface finish	skin		
Squareness	5	mm/m	EN 824
Thickness tolerance	+2/-2 (< 50 mm) +3/-2 (≥ 50 mm)	mm	EN 823
Width tolerance	+/- 8	mm	EN 822
Length tolerance	+/- 10	mm	EN 822
Edge profile	 butt		