Technical Information Sheet



QuickSeam™ SA Flashing

1. Description

Firestone QuickSeam™ SA Flashing is a 457 mm (18") wide, 1.5 mm thick non-reinforced RubberCover™ EPDM membrane, fully laminated to Firestone QuickSeam Tape. It has a polyester release liner for easy removal and excellent weather resistance. The SA Flashing can be used to easily flash details where cured EPDM is required or preferred: curbs, parapets, gutters, general roof repairs, drain and pipe flanges.



2. Preparation

The RubberCover™ EPDM surfaces and/or mating surfaces must be prepared with QuickPrime™ Plus, using a QuickScrubber™. Use of other products is not allowed. Restore the product to room temperature prior to use if exposed to temperatures below 15°C for prolonged periods.

3. Application

Apply the strip in one or two dimensions (flat or maximum one angle change). Refer to the Firestone guidelines for specific installation instructions.

4. Coverage

In accordance with length of detail to be covered.

5. Characteristics

Physical

- Superior ozone and UV resistance.
- Remains flexible over wide temperature variations.
- Application temperature range is between -20°C and 50°C.
- Outstanding adhesion to approved substrates for maximum performance.

			п			
				Ta1	ica	-11
-	lЧ	. –			l H	e


		EPDM Membrane	QuickSeam Tape
•	Base	EPDM	Rubber polymers
•	Color	Black	Black
•	Solvents	None	None
•	Solids	100%	100%
•	State	Cured	Cured
•	Thickness	1.5 mm	0.5 mm
•	Width	457 mm	460 mm

6. Packaging / Storage / Shelf Life

Packaging	15.25 m (50') rolls, 1 roll per carton				
Part number	W56RAC1620				

Note: QuickScrubber and/or QuickScrubber Plus pads and handles are included in each carton. Quantities vary depending on the QuickSeam product.

Storage: Store in original unopened containers at temperatures between 15°C and 25°C, in a well-ventilated place. Keep the material dry and out of direct sunlight until ready for application.



Technical Information Sheet



Shelf life: 24 months can be expected if stored in above-mentioned conditions. Verify production date on each roll. Shelf life will be reduced if exposed to higher temperatures. Shelf life information is only a recommendation and not a fact of life. The real expiration date highly depends on the history of storage and handling of the accessories.

7. Precautions

Refer to Safety Data Sheet.

This document replaces any other document published previous. This sheet is meant to highlight Firestone product information based on latest knowledge and experience and is subject to change without notice (check the Firestone website for latest document version). Above mentioned values are based on tested samples and may vary within applicable tolerances. Firestone takes responsibility for furnishing quality materials which meet published Firestone product specifications. No Firestone representative is authorized to vary this disclaimer.



RC_LIT_TIS_EN_QS SA Flashing | 10-2020